

(19) 世界知的所有権機関
国際事務局(43) 国際公開日
2005年9月1日 (01.09.2005)

PCT

(10) 国際公開番号
WO 2005/080658 A1(51) 国際特許分類: D04H 1/42,
D01F 6/62, 8/06, D04H 1/72

(21) 国際出願番号: PCT/JP2005/003541

(22) 国際公開日: 2005年2月23日 (23.02.2005)

(25) 国際出願の言語: 日本語

(26) 国際公開の言語: 日本語

(30) 優先権データ:
特願2004-045804 2004年2月23日 (23.02.2004) JP(71) 出願人(米国を除く全ての指定国について): 帝人ファイバー株式会社 (TELJIN FIBERS LIMITED) [JP/JP];
〒5410054 大阪府大阪市中央区南本町1丁目6番7号
Osaka (JP).


(72) 発明者; および

(75) 発明者/出願人(米国についてのみ): 合田 裕憲
(GODA, Hironori) [JP/JP]; 〒7918041 愛媛県松山市北
吉田町77番地 帝人ファイバー株式会社 松山事業
所内 Ehime (JP). 山本 信幸 (YAMAMOTO, Nobuyuki)[JP/JP]; 〒7918041 愛媛県松山市北吉田町77番地
帝人ファイバー株式会社 松山事業所内 Ehime (JP).(74) 代理人: 青木 篤, 外(AOKI, Atsushi et al.); 〒1058423
東京都港区虎ノ門三丁目5番1号 虎ノ門37森ビ
ル 青和特許法律事務所 Tokyo (JP).(81) 指定国(表示のない限り、全ての種類の国内保護が
可能): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR,
BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM,
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU,
ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS,
LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA,
NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE,
SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.(84) 指定国(表示のない限り、全ての種類の広域保護
が可能): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA,
SD, SL, SZ, TZ, UG, ZM, ZW), ユーラシア (AM, AZ,
BY, KG, KZ, MD, RU, TJ, TM), ヨーロッパ (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,

/続葉有/

(54) Title: SYNTHETIC STAPLE FIBER FOR AIRLAID NONWOVEN FABRIC

(54) 発明の名称: エアレイド不織布用合成短繊維



(57) Abstract: A synthetic staple fiber for an airlaid nonwoven fabric, characterized in that it has a fiber length of 0.1 to 45 mm and a cross-sectional shape having 1 to 30 concave portions wherein the concave portion has a ratio (D/L) of the maximum depth (D) to the maximum opening width (L) in the range of 0.1 to 0.5. The above synthetic staple fiber exhibits good air opening characteristics and is suitable for producing an airlaid nonwoven fabric having excellent quality.

(57) 要約: 空気開繊性が良好であり、かつ品質に優れたエアレイド不織布を製造するのに好適な合成短繊維は、0.1~45mmの繊維長と1~30個の凹部を有する横断面形状を有し、この横断面形状において前記凹部の最大深さDの、最大開口部幅Lに対する比D/Lが0.1~0.5の範囲内にある。



IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR),
OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML,
MR, NE, SN, TD, TG).

— 請求の範囲の補正の期限前の公開であり、補正書受領の際には再公開される。

添付公開書類:

— 国際調査報告書

2文字コード及び他の略語については、定期発行される各PCTガゼットの巻頭に掲載されている「コードと略語のガイダンスノート」を参照。